

Druck/Temperaturverlauf für Flansche nach DIN 2527/2627-2638 in 1.4404/35 / 1.4571

Nenndruck PN	Druck bei entsprechender Temperatur in [bar]					
	< 120°C 100%	< 200°C 87.50%	< 250°C 80%	< 300°C 70%	< 350°C 60%	< 400°C 50%
10	10	8.7	8	7	6	5
16	16	14	12.8	11.2	9.6	8
25	25	21.8	20	17.5	15	12.5
40	40	35	32	28	24	20
64	64	56	51.2	44.8	38.4	32
100	100	87.5	80	70	60	50
160	160	140	128	112	96	80
250	250	218.7	200	175	150	125
320	320	280	256	224	192	160
400	400	350	320	280	240	200

